

**This Page Is Inserted by IFW Operations
and is not a part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- **BLACK BORDERS**
- **TEXT CUT OFF AT TOP, BOTTOM OR SIDES**
- **FADED TEXT**
- **ILLEGIBLE TEXT**
- **SKEWED/SLANTED IMAGES**
- **COLORED PHOTOS**
- **BLACK OR VERY BLACK AND WHITE DARK PHOTOS**
- **GRAY SCALE DOCUMENTS**

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



Europäisches Patentamt
European Patent Office
Office européen des brevets



⑪ Publication number : 0 107 635 B2

⑫

NEW EUROPEAN PATENT SPECIFICATION

⑬ Date of publication of the new patent specification : 17.03.93 Bulletin 93/11

⑭ Application number : 83870081.3

⑮ Date of filing : 19.08.83

⑯ Int. Cl.⁵ : B29C 35/00, C08L 23/16,
C08L 23/02, C08J 3/24

⑰ Process for the preparation of thermoplastic elastomers.

⑱ Priority : 23.08.82 US 410196

⑲ Date of publication of application :
02.05.84 Bulletin 84/18

⑳ Publication of the grant of the patent :
23.09.87 Bulletin 87/39

㉑ Mention of the opposition decision :
17.03.93 Bulletin 93/11

㉒ Designated Contracting States :
BE DE FR GB IT NL

㉓ References cited :
EP-A- 0 072 203
DE-A- 1 445 228
DE-A- 1 520 152
DE-A- 1 694 804
DE-A- 2 848 448
DE-B- 1 445 228
GB-A- 2 007 683
US-A- 3 037 954
US-A- 3 957 919
US-A- 3 963 679
US-A- 4 088 714
US-A- 4 104 210
US-A- 4 116 914

㉔ References cited :

US-A- 4 130 535
US-A- 4 141 878
US-A- 4 271 049
US-A- 4 299 931

W & P Brochures a) Aufbereitung und Verarbeitung von Elastomer, Vortrag vom 5.10.79, Venedig b) W & P f. Techn. Continua c) Alloying of PP with EPDM d) KCVt Kurz-Information Several brochures and other publications issued by the Company W & P
G. Alliger "Vulcanization of Elastomers", Reinhold Publishing Corporation, New York, page 289

㉕ Proprietor : Monsanto Company
Patent Department 800 North Lindbergh
Boulevard
St. Louis Missouri 63167-7020 (US)

㉖ Inventor : Abdou-Sabet, Sabet
188 Benson Road
Akron Ohio 44313 (US)
Inventor : Shen, Kuo-Shein
442 Bath Hills Blvd
Akron Ohio 44313 (US)

㉗ Representative : TER MEER - MÖLLER -
STEINMEISTER & PARTNER
Mauerkircherstrasse 45
W-8000 München 80 (DE)

EP 0 107 635 B2

Description

This application relates to dynamic vulcanization processes for the preparation of thermoplastic elastomers comprising a blend of plastic and cured rubber, and the products prepared by said processes.

Dynamic vulcanization is a process whereby a blend of plastic, rubber and rubber curative is masticated while curing the rubber. The term "dynamic" indicates the mixture is subjected to shear forces during the vulcanization step as contrasted with "static" vulcanization wherein the vulcanizable composition is immobile (in fixed relative space) during the vulcanization step. One advantage of dynamic vulcanization is that elastoplastic (thermoplastic elastomeric) compositions may be obtained when the blend contains the proper proportions of plastic and rubber. Examples of dynamic vulcanization are described in US-A-4 130 535 and US-A-4 311 628, the latter being equivalent to GB-A-2 007 683 cited in the European Search Report. GB-A-2 007 683 discloses elastoplastic compositions comprising blends of thermoplastic crystalline polyolefin resin and cured EPDM rubber, in which the rubber is cured with a phenolic curative, and a process for preparing such compositions in which the resin, rubber and curative are masticated at a temperature sufficient to soften or melt the polyolefin resin and for a time sufficient to obtain a homogeneous mixture, cure activator is added while continuing to masticate the mixture, and mastication is continued at curing temperature until the rubber is cured to the extent that no more than 5% of the rubber is extractable in boiling xylene.

Dynamic vulcanization processes using mixing equipment such as that disclosed in the foregoing prior art are not entirely satisfactory for making soft compositions because as the rubber level rises the resulting compositions become less fabricable, for example, the compositions give poor extrudates and, sometimes, cannot be extruded at all. Accordingly, there is a need for processes for preparing soft, extrusion-fabricable, thermoplastic elastomeric compositions.

GB-A-2 007 683 is considered to be the closest prior art under Article 54(2) EPC for the purposes of Article 54(1) and Article 56 EPC. For all designated states except Belgium, this art is supplemented under Article 54(3) EPC by EP-A-0 072 203 for the purposes of Article 54(1) EPC.

EP-A-0 072 203 discloses a process for the production of a partially cross-linked rubber-resin composition by directly feeding a particulate peroxide-curable olefin copolymer rubber and a peroxide decomposing polyolefin resin with an organic peroxide compound to a twin screw extruder so that the rubber and the resin are thereby subjected to dynamic heat treatment in the presence of the peroxide.

In view of adapting the description to this new claim 1, it is requested to substitute the sentence in page 2, lines 31 to 34 by the following:

"According to the present invention, it has been discovered that an improved thermoplastic elastomer composition comprising a blend of plastic and cured rubber which comprises 50 weight percent or less of plastic is obtained by

- (a) masticating plastic, rubber and other compounding ingredients in the first third of an extruder to melt the plastic and form an essentially homogenous blend in the absence of a cure activator and
- (b) dynamically vulcanizing said essentially homogenous blend and a rubber curative in the presence of a cure activator in the last two thirds of the extruder by masticating for a period of two minutes or less at a shear rate of at least 2000 sec⁻¹ so that the rubber is cured to the extent that no more than 5 weight-% of the rubber is soluble in a rubber solvent."

Vulcanization is considered to be essentially complete when no more than 5 weight percent of the rubber is soluble in a rubber solvent. Preferably, the blend is subjected during vulcanization to a shear rate of about 2500 to 7500 sec⁻¹. The thermoplastic elastomeric composition so produced exhibits superior tensile properties including higher strength and greater elongation and (depending upon the amount of rubber) also exhibits better fabricability, i.e., its draw-down ratio is higher indicating better extrudability. Moreover, extrudable compositions containing high proportions of rubber can be produced by the process of the invention, whereas identical blends dynamically vulcanized at low shear rates (for example, the level of shear obtained in Banbury mixers) are non-extrudable compositions.

The process of the invention is applicable to an blend of plastic, rubber and rubber curative. Of course, it is understood that the plastic and rubber must be compatible or compatibilizable by a compatibilizing agent such as, a block copolymer or graft polymer. Any rubber curative suitable for dynamic vulcanization and suitable for the particular rubber is satisfactory for the process of this invention. For examples, of suitable plastics, rubbers, and rubber curatives refer to the patents mentioned under the Background of the Invention.

It is further understood that compositions suitable for the practice of the invention contain ingredients other than rubber and plastic, for example, particulate fillers, carbon black, clay, silica, plasticizers, extender oils, antidegradants, stabilizers, and components normally compounded in blends of plastic and rubber. The process is suitable for compositions having a melt viscosity of 10 to 200 pascal seconds and is especially suitable for compositions having a melt viscosity of 10 to 100 pascal seconds. The melt viscosity is the viscosity at the

shear rate of 2000 sec^{-1} to $10,000 \text{ sec}^{-1}$ of a homogeneous blend comprising rubber, plastic and all other compounding ingredients, with the plastic in a molten condition, typically at about $170^{\circ}\text{--}230^{\circ}\text{C}$. The melt viscosity of a blend can be reduced by adding extender oil or plasticizer or both.

The process of the invention is suitable for compositions comprising a blend of plastic and rubber which comprises 50 weight percent or less of plastic. The relative proportions of plastic and rubber cannot be clearly delineated because the limits vary due to the nature and type of plastic and rubber involved and the type and amounts of other ingredients, such as, extender oil, plasticizer and particulate fillers. Generally, the process of the invention is especially advantageous for compositions comprising a blend of 60-85 parts by weight of rubber and correspondingly, 40-15 parts by weight of plastic. The process is especially advantageous for the preparation of extrudable blends comprising 70-80 parts by weight of EPDM rubber and correspondingly, 30-20 parts by weight of polypropylene. A more preferred blend contains 1-1.5 parts by weight of extender oil per part by weight of EPDM rubber.

One advantage of the process of the invention is that vulcanization is essentially complete in two minutes or less. At shear rates of 2500 sec^{-1} or more, vulcanization is complete within 20-60 seconds. Since output increases with decreasing residence times, short residence time in the mixer results in greater production efficiency. Shorter residence times also means less degradation of thermally unstable plastics and rubbers.

Any mixer capable of generating a shear rate of 2000 sec^{-1} or higher is suitable for carrying out the process of the invention. Generally, this requires a high speed internal mixer having a narrow clearance between the tips of the kneading elements and the wall. Shear rate is the velocity gradient in the space between the tip and the wall. Depending upon the clearance between the tip and the wall, rotation of the kneading elements from about 100 to 500 revolutions per minute (rpm) is generally adequate to develop a sufficient shear rate. Depending upon the number of tips on a given kneading element and the rate of rotation, the number of times the composition is kneaded by each element is about 1 to 30 times per second, preferably about 5 to 30 times per second, and more preferably about 10 to 30 times per second. This means that material typically is kneaded from about 200 to 1800 times during vulcanization. For example, in a typical process with a rotor with three tips rotating at 400 rpm in a mixer having a residence time of 30 seconds, the material will be kneaded 600 times.

A mixer satisfactory for carrying out the process of the invention is a high shear mixing extruder produced by Werner & Pfleiderer, Germany. The Werner & Pfleiderer (WP) extruder is a twin-shaft screw extruder in which two intermeshing screws rotate in the same direction. Details of such extruders are described in U.S. Patents 3,963,679 and 4,250,292; and German Patents 2,302,548; 2,473,764 and 2,549,372.

Screw diameters vary from 53 mm to 300 mm; barrel lengths vary but generally the maximum barrel length is the length necessary to maintain a length over diameter ratio of 42. The shaft screws of these extruders normally are made-up of alternating series of conveying sections and kneading sections. The conveying sections cause material to move forward from each kneading section of the extruder. Typically, there are about an equal number of conveying and kneading sections fairly evenly distributed along the length of the barrel. Kneading elements containing one, two, three or four tips are suitable, however, kneading elements 5-30 mm wide having three tips are preferred. At recommended screw speeds of 100-600 rpm and radial clearance of 0.1 to 0.4 mm, these mixing extruders provide shear rates of at least 2000 sec^{-1} to 7500 sec^{-1} or more. The net mixing power expended in the process of the invention including homogenization and dynamic vulcanization is usually about 100-500 watt hours per kilogram of product produced; with about 300-400 watt hours per kilogram being typical.

Description of the preferred embodiments

The process of the invention is illustrated by the use of W&P twin screw extruders, models ZSK-53 or ZSK-83. Unless specified otherwise, all of the plastic, rubber and other compounding ingredients except cure activator are fed into the entry port of the extruder. In the first third of the extruder, the composition is masticated to melt the plastic and to form an essentially homogeneous blend. Cure activator (vulcanization accelerator) is added through another entry port located about one-third of the length of the barrel downstream from the initial entry port. The last two-thirds of the extruder (from the cure activator entry port to the outlet of the extruder) is regarded as the dynamic vulcanization zone. A vent operated under reduced pressure is located near the outlet to remove any volatile by-products. Sometimes, additional extender oil or plasticizer and colorants are added at another entry port located about the middle of the vulcanization zone.

The residence time within the vulcanization zone is the time a given quantity of material is within the fore-said vulcanization zone. Since the extruders are typically operated under a starved condition, usually about 60 to 80 percent full, residence time is essentially directly proportional to feed rate. Thus, residence time in the vulcanization zone is calculated by multiplying the total volume of the dynamic vulcanization zone times

the fill factor divided by the volume flow rate. Shear rate is calculated by dividing the product of the circumference of the circle generated by the screw tip times the revolutions of the screw per second by the tip clearance. In other words, shear rate is the tip velocity divided by the tip clearance.

Polypropylene/EPDM rubber blends are used to illustrate the invention. The blends comprise (all parts by weight) 100 parts by EPDM rubber (4.5 wt.% ethylidene norbornene), 37 parts of kaolin clay, 130 parts of extender oil, 5 parts of titanium dioxide, 5 parts of wax, 2 parts of zinc oxide, 10 parts of methylol phenol curing resin and varying amounts of polypropylene, PP, (Profex 6723) as indicated in Table 1. In addition, 1.68 parts of stannous chloride cure activator is added to activate the vulcanization reaction. The compositions after homogenization before addition of cure activator have a melt viscosity of about 60 to 80 pascal seconds at about 200°C and at a shear rate of about 2000 sec^{-1} . After vulcanization, the compositions have a melt viscosity of about 80 to 100 pascal seconds at the same temperature and shear rate.

The aforesaid blend compositions are fed at 83 to 116 Kg per hour depending upon the amount of polypropylene added to a WEP ZSK-53 Extruder having a screw tip clearance of about 0.2 mm. The screw speed is 300 rpm. The temperature along the vulcanization zone is 180 to 230°C. The shear rate is 4850 sec^{-1} between the screw tip and the barrel wall. The residence time in the dynamic vulcanization zone varies from 32 to 42 seconds. The thermoplastic elastomeric composition exiting from the extruder is pelletized and the pellets are injection molded to form plaques from which properties are measured. Compositions containing identical components are prepared in a 1-A Banbury mixer at about 197°C dump temperature. Residence times of about 4-4.5 minutes after addition of the curative system are required to complete vulcanization. The rotor speed is about 110 rpm and the shear rate is about 360 sec^{-1} . Except for the Banbury run of Example 1 which could not be extruded, the product is pelletized and the pellets are injection molded to form plaques from which properties are measured. Measurements in parenthesis of Example 1, are measured from plaques prepared by compression molding. Rod draw-down ratio is the ratio of the velocity a rod shaped extrudate issuing from a 4.7 mm diameter orifice at 190°C and the velocity of the extrudate at break when subjected to a constant increase in velocity by increasing the rate of revolution of a take-up drum. The data is summarized in Table 1.

TABLE 1

Example No.	1	2	3	4	5	6
Mixer	Banbury	Banbury	Banbury	Banbury	Banbury	Banbury
Rate kg/hr	74	74	74	74	74	74
Polypropylene, phr.	32.5	38	58.5	88	152	223
Rubber/PP ratio	75.5	72.5	63	53	40	31
	24.5	27.5	37	47	60	89
Residence time, sec	240	240	240	240	240	240
Properties						
TS, MPa	—	3.8	8.8	11.2	15.2	18.3
	(4.9)					
M ₁₀₀ , MPa	—	2.1	3.8	4.6	8.3	9.0
	(2.1)					
Elong., %	—	240	380	450	510	570
	(270)					
Tension set, %	—	5	10	13	17	23
	(3)					
Hardness	—	63A	71A	81A	82A	89A
	(57A)					
TSB, MPa	—	13	42	63	78	94
	(18)					
Rod drawn-down	—	1.1	2.7	4.0	5.3	7.8
	(0)					

The data indicate that the thermoplastic elastomeric compositions produced under high shear exhibit superior tensile properties over the entire range of plastic/rubber ratio. The draw-down data indicate that the process of the invention involving high shear dynamic vulcanization improves the fabricability (extrudability) of compositions containing higher proportions of rubber (Example 1-4). The compositions of Example 1 prepared under low shear conditions in the Banbury mixer was not fabricable by extrusion, but it will form a sheet on a mill and can be compression molded. Comparison of the compression molded properties of Example 1 show that the process of the invention results not only in a fabricable product but also superior tensile properties.

The process of the invention using a ZSK-83 WP extruder mixer at a shear rate of about 5000 sec⁻¹ gives extrudable compositions within the range of 55-65 Shore A hardness, whereas, a process using a 3D Banbury mixer at a shear rate of about 360 sec⁻¹ and the same ingredients and proportions of ingredients gives non-extrudable compositions.

Claims

1. A process for preparing a thermoplastic elastomer composition comprising a blend of plastic and cured rubber by which comprises 50 weight percent or less of plastic
 - a) masticating plastic, rubber and other compounding ingredients in the first third of an extruder to melt the plastic and form an essentially homogenous blend in the absence of a cure activator and
 - b) dynamically vulcanizing said essentially homogenous blend and a rubber curative in the presence of a cure activator in the last two thirds of the extruder by masticating for a period of 2 minutes or less at a shear rate of at least 2000 sec⁻¹ so that the rubber is cured to the extent that no more than 5 weight percent of the rubber is soluble in a rubber solvent.
2. The process of Claim 1 in which the melt viscosity of the composition is 10 to 200 pascal seconds.
3. The process of Claim 2 in which the shear rate is 2500 to 7500 sec⁻¹.
4. The process of Claim 3 in which the composition has a melt viscosity of 10 to 100 pascal seconds.
5. The process of Claim 4 in which the composition comprises a blend of 60-85 parts by weight of rubber and correspondingly, 40-15 parts by weight of plastic.
6. The process of Claim 5 in which the plastic is polypropylene and the rubber is EPDM rubber.
7. The process of Claim 6 in which the composition comprises a blend of 70-80 parts by weight of EPDM rubber and correspondingly, 30-20 parts by weight of polypropylene.
8. The process of either of Claims 6 and 7 in which the composition contains 1-1.5 parts of extender oil per part of EPDM rubber.
9. The process of any of Claims 6 to 8 in which the curative for the rubber is a phenolic curative comprising phenolic resin and cure activator.
10. The process of any of Claims 6 to 9 in which the blend is masticated by the use of a twin-shaft screw extruder in which two intermeshing screws rotate in the same direction.

Patentansprüche

1. Verfahren zur Herstellung einer thermoplastischen Elastomermasse in Form einer Mischung aus einem Kunststoff und einem gehärteten Kautschuk, welche 50 Gew. -% oder weniger Kunststoff enthält, durch
 - a) Mastizieren von Kunststoff, Kautschuk und anderen Mischungsbestandteilen im ersten Drittel eines Extruders, um den Kunststoff zu schmelzen und eine im wesentlichen homogene Mischung in Abwesenheit eines Härungsaktivators zu bilden, und
 - b) dynamisches Vulkanisieren der im wesentlichen homogenen Mischung und eines Kautschukhärters in Gegenwart eines Härungsaktivators in den letzten zwei Dritteln des Extruders durch Mastizieren während eines Zeitraums von 2 Minuten oder weniger bei einer Scherrate von mindestens 2000

sec⁻¹, so daß der Kautschuk in einem solchen Maße gehärtet wird, daß nicht mehr als 5 Gew.-% des Kautschuks in einem Kautschuklösungsmittel löslich sind.

2. Verfahren nach Anspruch 1, wobei die Schmetzviskosität der Masse 10 bis 200 Pascalsekunden beträgt.
3. Verfahren nach Anspruch 2, wobei die Scherrate 2500 bis 7500 sec⁻¹ beträgt.
4. Verfahren nach Anspruch 3, wobei die Masse eine Schmetzviskosität von 10 bis 100 Pascalsekunden besitzt.
5. Verfahren nach Anspruch 4, wobei die Masse eine Mischung aus 60-85 Gewichtsteilen Kautschuk und entsprechend 40-15 Gewichtsteilen Kunststoff umfaßt.
6. Verfahren nach Anspruch 5, wobei als Kunststoff Polypropylen und als Kautschuk EPDM-Kautschuk verwendet werden.
7. Verfahren nach Anspruch 6, wobei die Masse eine Mischung aus 70-80 Gewichtsteilen EPDM-Kautschuk und entsprechend 30-20 Gewichtsteilen Polypropylen umfaßt.
8. Verfahren nach einem der Ansprüche 6 und 7, wobei die Masse 1-1,5 Teile eines Strecköls pro Teil EPDM-Kautschuk enthält.
9. Verfahren nach einem der Ansprüche 6 bis 8, wobei als Härter für den Kautschuk ein phenolischer Härter verwendet wird, der ein Phenolharz und einen Härungsaktivator umfaßt.
10. Verfahren nach einem der Ansprüche 6 bis 9, wobei die Mischung unter Anwendung eines Doppelschneckenextruders, dessen beide kühnenden Schnecken in gleicher Richtung gedreht werden, mastiziert wird.

Revendications

1. Procédé de préparation d'une composition élastomère thermoplastique comprenant un mélange de plastique et de caoutchouc vulcanisé qui comporte 50 % en poids ou moins de plastique en :
 - (a) mastiquant du plastique, du caoutchouc et d'autres ingrédients de mélange dans le premier tiers d'une extrudeuse afin de fondre le plastique et former un mélange essentiellement homogène en l'absence d'un activateur de vulcanisation, et
 - (b) vulcanisant dynamiquement ledit mélange essentiellement homogène et un agent de vulcanisation du caoutchouc en présence d'un activateur de vulcanisation dans les deux derniers tiers de l'extrudeuse par masticage d'une durée de deux minutes ou moins à un gradient de cisaillement d'au moins 2000 sec⁻¹ de façon que le caoutchouc soit vulcanisé au point que pas plus de 5 % en poids du caoutchouc soient solubles dans un solvant du caoutchouc.
2. Procédé selon la revendication 1, dans lequel la viscosité à l'état fondu de la composition est de 10 à 200 pascal.secondes.
3. Procédé selon la revendication 2, dans lequel le gradient de cisaillement est de 2500 à 7500 sec⁻¹.
4. Procédé selon la revendication 3, dans lequel la composition a une viscosité à l'état fondu de 10 à 100 pascal.secondes.
5. Procédé selon la revendication 4, dans lequel la composition comprend un mélange de 60 à 85 parties en poids de caoutchouc, et par conséquent de 40 à 15 parties en poids de plastique.
6. Procédé selon la revendication 5, dans lequel le plastique est du polypropylène et le caoutchouc est un caoutchouc EPDM.
7. Procédé selon la revendication 6, dans lequel la composition comprend un mélange de 70 à 80 parties en poids de caoutchouc d'EPDM, et par conséquent de 30 à 20 parties en poids de polypropylène.

8. Procédé selon l'une quelconque des revendications 6 et 7, dans lequel la composition contient 1 à 1,5 partie d'huile de dilution par partie de caoutchouc EPDM.
9. Procédé selon l'une quelconque des revendications 6 à 8, dans lequel l'agent de vulcanisation pour le caoutchouc est un agent de vulcanisation phénolique comprenant une résine phénolique et un activateur de vulcanisation.
10. Procédé selon l'une quelconque des revendications 6 à 9, dans lequel le mélange est masticqué en utilisant une extrudeuse biva dans laquelle les deux vis engrangent tourment dans le même sens.